

1 **(January 5, 2004)**

2 ***Strip Seal Expansion Joint System***

3 The metal components shall conform to ASTM A 36, ASTM A 992, or ASTM A 572, and  
4 shall be protected against corrosion by one of the following methods:

- 5
- 6 1. Zinc metallized in accordance with the Special Provision **METALLIC**  
7 **COATINGS**.
- 8
- 9 2. Hot-dip galvanized in accordance with AASHTO M 111.
- 10
- 11 3. Paint in accordance with Section 6-07.3(1). The color of the final coat shall be  
12 Washington Gray. The surfaces embedded in concrete shall be painted only  
13 with a shop coat of inorganic zinc silicate paint.  
14

15 The strip seal gland shall be continuous for the full length of the joint with no splices  
16 permitted, unless otherwise shown in the Plans.